

ABS XG569C

Injection Molding

Description

Anti-Scratch, High Gloss

Application

LCD TV Front Cabinet, Bezel
Audio/Video Housing

Properties	Test Condition	Test Method	Unit	Typical Value
Physical				
Specific Gravity		ASTM D792	-	1.11
Molding Shrinkage (Flow), 3.2mm		ASTM D955	%	0.2~0.4
Melt Flow Rate	220℃/10kg	ASTM D1238	g/10min	11.5
Water Absorption	23℃, 24hrs	ASTM D570	%	0.3
Mechanical				
Tensile Strength, 3.2mm		ASTM D638		
@ Yield	50mm/min		kg/cm ²	560
Tensile Elongation, 3.2mm		ASTM D638		
@ Yield	50mm/min		%	>6
@ Break	50mm/min		%	20
Tensile Modulus, 3.2mm	1mm/min	ASTM D638	kg/cm ²	
Flexural Strength, 6.4mm	15mm/min	ASTM D790	kg/cm ²	920
Flexural Modulus, 6.4mm	15mm/min	ASTM D790	kg/cm ²	28,500
Tear Strength @ Break	50mm/min	ASTM D624	kg/cm	
IZOD Impact Strength, 6.4mm		ASTM D256		
(Notched)	23℃		kg·cm/cm	10
	-30℃		kg·cm/cm	5
IZOD Impact Strength, 3.2mm		ASTM D256		
(Notched)	23℃		kg·cm/cm	10
	-30℃		kg·cm/cm	5
Rockwell Hardness	R-Scale	ASTM D785	-	116
Thermal				
Heat Deflection Temperature, 6.4mm		ASTM D648		
(Unannealed)	18.6kg		℃	83
	4.6kg		℃	88
Heat Deflection Temperature, 3.2mm		ASTM D648		
(Unannealed)	18.6kg		℃	82
	4.6kg		℃	86
Flammability		UL94		
1.6mm			class	HB
3.2mm			class	HB
Others				
Ozone Resistance	5sec	JIS K6301	-	No Crack

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection moulded specimens and after 48 hours storage at 23℃, 50% relative humidity.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

ABS XG569C

Injection Molding

Description

Anti-Scratch, High Gloss

Application

LCD TV Front Cabinet, Bezel
Audio/Video Housing

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value	
Drying Temperature	°C	80 ~ 90	
Drying Time	hrs	3 ~ 4	
Minimum Moisture Content	%	0.01	
Melt Temperature	°C	200 ~ 230	
Cylinder Temperature	Rear	°C	180 ~ 200
	Middle	°C	190 ~ 210
	Front	°C	200 ~ 220
Nozzle Temperature	°C	200 ~ 230	
Mold Temperature	°C	40 ~ 60	
Back Pressure	kg/cm ²	300 ~ 600	
Screw Speed	rpm	30 ~ 60	

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！