

Cycolac* Resin MG37EP
Americas: COMMERCIAL

Injection molding abs, especially for electroplating/painting applications requiring excellent flow and aesthetics.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	430	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	340	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	30	%	ASTM D 638
Tensile Modulus, 5 mm/min	24200	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	740	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	24900	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	2.4	%	ISO 527
Tensile Strain, break, 50 mm/min	42.8	%	ISO 527
IMPACT			
Izod Impact, notched, 23°C	35	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	350	cm-kgf	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	31	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	34	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	101	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	98	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	85	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.74E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.38E-05	1/°C	ASTM E 831
Vicat Softening Temp, Rate B/50	96	°C	ISO 306

¹ Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

² Only typical data for material selection purpose. Not to be used for part or tool design.
³ This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
⁴ Own measurement according to UL.
⁵ Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布，我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

Cycolac* Resin MG37EP
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
Vicat Softening Temp, Rate B/120	98	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	79	°C	ISO 75/Af
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.05	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.4 - 0.6	%	SABIC Method
Melt Flow Rate, 230°C/3.8 kgf	4.4	g/10 min	ASTM D 1238
Melt Viscosity, 240°C, 1000 sec-1	2550	poise	ASTM D 3825
Density	1.04	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	16	g/10 min	ISO 1133
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	3	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.52	mm	UL 94

¹ Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 230C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

² Only typical data for material selection purpose. Not to be used for part or tool design.
³ This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
⁴ Own measurement according to UL.
⁵ Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布, 我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

Cycolac* Resin MG37EP
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	80 - 95	°C
Drying Time	2 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	255 - 280	°C
Nozzle Temperature	255 - 280	°C
Front - Zone 3 Temperature	250 - 270	°C
Middle - Zone 2 Temperature	230 - 245	°C
Rear - Zone 1 Temperature	215 - 230	°C
Mold Temperature	40 - 80	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm
Shot to Cylinder Size	50 - 70	%
Vent Depth	0.038 - 0.051	mm

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.
5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布，我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！