

Elastollan® B 95 A 11U

Thermoplastic Polyurethane Elastomer (Polyester)

Elastogran GmbH

General	
Material Status	• Commercial: Active
Availability	• Europe
Additive	• UV Stabilizer
Forms	• Pellets

Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm ³	ISO 1183

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	54.0	MPa	ISO 527-2
Tensile Strain (Break)	500	%	ISO 527-2

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	11.2	MPa	
300% Strain	12.9	MPa	
Tear Strength	120	kN/m	ISO 34-1

Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A	95		
Shore D	47		

Additional Information
 Note: These properties were tested in accordance with the DIN test standard.
 Stress at 20% elongation, DIN 53504: 7.7 Mpa
 Abrasion Loss, DIN 53516: 35 mm³

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！