

Elastollan® B 98 A 11

Thermoplastic Polyurethane Elastomer (Polyester)

Elastogran GmbH

General	
Material Status	• Commercial: Active
Availability	• Europe
Forms	• Pellets

Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm ³	ISO 1183

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	140	MPa	ISO 527-2
Tensile Stress (Break)	55.0	MPa	ISO 527-2
Tensile Strain (Break)	500	%	ISO 527-2

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	12.0	MPa	
300% Strain	30.0	MPa	
Tear Strength	130	kN/m	ISO 34-1
Compression Set			ISO 815
23°C	35	%	
70°C	45	%	

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	50		ISO 868

Additional Information

Note: These properties were tested in accordance with the DIN test standard.
 Stress at 20% elongation, DIN 53504: 8 Mpa
 Abrasion Loss, DIN 53516: 25 mm³
 Tensile Strength After Storage in Water, DIN 53504, 80°C for 21 days: 45 Mpa
 Elongation at Break After Storage in Water, DIN 53504, 80°C for 21 days: 500 %

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！