

# Elastollan® S 60 A 10WH

Thermoplastic Polyurethane Elastomer (Polyester)  
Elastogran GmbH

General	
Material Status	• Commercial: Active
Availability	• Europe
Additive	• Plasticizer
Forms	• Pellets

Physical	Nominal Value	Unit	Test Method	
Density	1.19	g/cm <sup>3</sup>	ISO 1183	
Mechanical		Nominal Value	Unit	Test Method
Tensile Stress (Break)	33.0	MPa	ISO 527-2	
Tensile Strain (Break)	850	%	ISO 527-2	
Elastomers		Nominal Value	Unit	Test Method
Tear Strength	35	kN/m	ISO 34-1	
Hardness		Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	60		ISO 868	

#### Additional Information

Note: These properties were tested in accordance with the DIN test standard.  
Abrasion Loss, DIN 53516: 60 mm<sup>3</sup>

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！