

# Ultraform® FK66003

Acetal (POM) Copolymer

BASF Corporation

## Product Description

Polyoxymethylene based batch with approx. 20 weight % silicone (polysiloxane) for modifying tribological properties of thermoplastic polyoxymethylenes. Recommended concentrations of batch FK66003 within the mixture with thermoplastic polyoxymethylenes are in the range of 1 to 5 %.

## General

Material Status	• Commercial: Active
Availability	• Europe
Additive	• Silicone Lubricant (20%)
Uses	• Plastics Modification
RoHS Compliance	• RoHS Compliant
Forms	• Granules
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• POM

Physical	Nominal Value	Unit	Test Method
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	35.0	cm <sup>3</sup> /10min	ISO 1133

  

Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	165	°C	ISO 3146

## Additional Information

The value listed as Melting Temperature (DSC), ISO 3146, was tested in accordance with ISO 3146.  
POM-K

Injection	Nominal Value	Unit
Processing (Melt) Temp	190 to 230	°C

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！