

# Ultraform® N2320 003 UNC Q600

Acetal (POM) Copolymer  
BASF Corporation

**Product Description**  
Ultraform N 2320 003 UNC Q600 is a rapidly freezing general-purpose injection-molding POM grade. It contains a mold release agent.

General			
Material Status	• Commercial: Active		
Availability	• North America		
Additive	• Mold Release		
Features	• General Purpose		
Uses	• Caps	• Gears	• Springs
Agency Ratings	• FDA 21 CFR 177.2470 • NSF 51	• NSF 61 • USP Class VI	
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		
Multi-Point Data	• Isochronous Stress vs. Strain (ISO 11403-1) • Isothermal Stress vs. Strain (ISO 11403-1) • Secant Modulus vs. Strain (ISO 11403-1)	• Shear Modulus vs. Temperature (ISO 11403-2) • Specific Heat vs. Temperature (ISO 11403-2) • Specific Volume vs. Temperature (ISO 11403-2)	• Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.40	g/cm <sup>3</sup>	ASTM D792
--	1400	kg/m <sup>3</sup>	ISO 1183 <sup>2</sup>
Melt volume-flow rate (190°C/2.16 kg)	7.50	cm <sup>3</sup> /10min	ISO 1133 <sup>2</sup>
Molding Shrinkage			
Flow: 3.18 mm	2.0	%	ASTM D955
Across Flow	2.1	%	ISO 294-4
Flow	2.1	%	ISO 294-4
Water Absorption			
Saturation	0.80	%	ASTM D570 ISO 62 <sup>2</sup>
Equilibrium, 50% RH	0.20	%	ASTM D570
Equilibrium	0.20	%	ISO 62 <sup>2</sup>

Mechanical	Nominal Value	Unit	Test Method
Tensile modulus	2700	MPa	ISO 527-2 <sup>2</sup>
Tensile Strength			
Yield, 23°C	65.0	MPa	ASTM D638
Yield, -40°C	93.0	MPa	ISO 527-2
Yield, 80°C	33.0	MPa	ISO 527-2
Yield	65.0	MPa	ISO 527-2 <sup>2</sup>
Tensile Elongation			
Yield, 23°C	9.4	%	ASTM D638
Yield	9.4	%	ISO 527-2 <sup>2</sup>
Nominal strain at break	27	%	ISO 527-2 <sup>2</sup>
Tensile Creep Modulus			ISO 899-1 <sup>2</sup>
1 hr	1800	MPa	
1000 hr	1400	MPa	
Flexural Modulus (23°C)	2470	MPa	ASTM D790

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

**Ultraform® N2320 003 UNC Q600**  
**Acetal (POM) Copolymer**  
**BASF Corporation**

Tuesday, December 15, 2009

Impact	Nominal Value	Unit	Test Method
Charpy notched impact strength			ISO 179/1eA <sup>2</sup>
-30°C	5.50	kJ/m <sup>2</sup>	
23°C	6.00	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179
-30°C	190	kJ/m <sup>2</sup>	
23°C	210	kJ/m <sup>2</sup>	
Notched Izod Impact			ASTM D256
-40°C	59.8	J/m	
23°C	69.4	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	154	°C	ASTM D648
1.8 MPa, Unannealed	99.0	°C	ASTM D648
1.8 MPa	100	°C	ISO 75-2 <sup>2</sup>
Melting Temperature	167	°C	ASTM D3418 ISO 3146
CLTE - Flow			
--	0.000060	cm/cm/°C	ASTM E831
--	0.00011	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity <sup>3</sup>	1.0E+13	ohms	ASTM D257 IEC 60093 <sup>2</sup>
Volume Resistivity			
1.50 mm	1.0E+13	ohm·cm	ASTM D257
--	1.0E+11	ohm·m	IEC 60093 <sup>2</sup>
Relative Permittivity			IEC 60250 <sup>2</sup>
100 Hz	3.80		
1 MHz	3.80		
Dissipation Factor			IEC 60250 <sup>2</sup>
100 Hz	10		
1 MHz	50		
Comparative tracking index	600		IEC 60112 <sup>2</sup>
Electric strength	40	kV/mm	IEC 60243-1 <sup>2</sup>
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 110	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.15	%	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	60.0 to 120	°C	
Injection Pressure	3.50 to 7.00	MPa	
Injection Rate	Fast		

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

<sup>3</sup> 1.5 mm

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！