

Ultraform® N2640 Z2 UNC Q600

Acetal (POM) Copolymer

BASF Corporation

Product Description

Ultraform N 2640 Z2 UNC Q600 is an elastomer-modified injection molding POM grade with high impact strength.

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Impact Modifier
Features	• High Impact Resistance • Impact Modified
Uses	• Automotive Exterior Parts • Fasteners • Toys
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding
Multi-Point Data	• Isochronous Stress vs. Strain (ISO 11403-1) • Shear Modulus vs. Temperature (ISO 11403-2) • Viscosity vs. Shear Rate (ISO 11403-2) • Isothermal Stress vs. Strain (ISO 11403-1) • Specific Heat vs. Temperature (ISO 11403-2) • Secant Modulus vs. Strain (ISO 11403-1) • Specific Volume vs. Temperature (ISO 11403-2)

Physical

	Nominal Value	Unit	Test Method
Specific Gravity	--	1.37 g/cm ³	ASTM D792
--	--	1370 kg/m ³	ISO 1183 ²
Melt volume-flow rate (190°C/2.16 kg)	7.00	cm ³ /10min	ISO 1133 ²
Molding Shrinkage			
Flow: 3.18 mm	1.9	%	ASTM D955
Across Flow	1.9	%	ISO 294-4
Flow	1.9	%	ISO 294-4
Water Absorption			
Saturation	0.80	%	ASTM D570 ISO 62 ²
Equilibrium, 50% RH	0.20	%	ASTM D570
Equilibrium	0.20	%	ISO 62 ²

Mechanical

	Nominal Value	Unit	Test Method
Tensile modulus	2000	MPa	ISO 527-2 ²
Tensile Strength			
Yield, 23°C	50.0	MPa	ASTM D638
Yield, -40°C	80.0	MPa	ISO 527-2
Yield	50.0	MPa	ISO 527-2 ²
Tensile Elongation			
Yield, 23°C	12	%	ASTM D638
Yield	12	%	ISO 527-2 ²
Nominal strain at break	45	%	ISO 527-2 ²
Tensile Creep Modulus			ISO 899-1 ²
1 hr	1550	MPa	
1000 hr	1050	MPa	
Flexural Modulus (23°C)	1970	MPa	ASTM D790

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

Ultraform® N2640 Z2 UNC Q600
Acetal (POM) Copolymer
BASF Corporation

Tuesday, December 15, 2009

Impact	Nominal Value	Unit	Test Method
Charpy notched impact strength			ISO 179/1eA ²
-30°C	6.50	kJ/m ²	
23°C	11.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	230	kJ/m ²	
23°C	No Break		
Notched Izod Impact			ASTM D256
-40°C	69.4	J/m	
23°C	120	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	140	°C	ASTM D648
1.8 MPa, Unannealed	85.0	°C	ASTM D648
1.8 MPa	85.0	°C	ISO 75-2 ²
Melting Temperature	167	°C	ASTM D3418 ISO 3146
CLTE - Flow			
--	0.000070	cm/cm/°C	ASTM E831
--	0.00012	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ³	1.0E+14	ohms	ASTM D257 IEC 60093 ²
Volume Resistivity			
1.50 mm	1.0E+12	ohm·cm	ASTM D257
--	1.0E+10	ohm·m	IEC 60093 ²
Relative Permittivity			IEC 60250 ²
100 Hz	4.00		
1 MHz	4.00		
Dissipation Factor			IEC 60250 ²
100 Hz	100		
1 MHz	140		
Comparative tracking index	600		IEC 60112 ²
Electric strength	40	kV/mm	IEC 60243-1 ²
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 110	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.15	%	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	60.0 to 120	°C	
Injection Pressure	3.50 to 7.00	MPa	
Injection Rate	Fast		

Notes

¹ Typical properties: these are not to be construed as specifications.

² Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

³ 1.5 mm

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！