

Ultramid® 1403-2 NF3001 (Cond)

Polyamide 66

BASF Corporation

Product Description

Ultramid 1403-2 NF3001 is a 13% glass reinforced, heat stabilized injection molding PA6/6.

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber Reinforcement, 13% Filler by Weight
Additive	• Heat Stabilizer
Features	• Good Dimensional Stability • Heat Stabilized
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Mechanical	Nominal Value	Unit	Test Method
Tensile modulus	3900	MPa	ISO 527-2 ²
Tensile Stress (Break)	90.0	MPa	ISO 527-2 ²
Tensile Strain (Break)	13	%	ISO 527-2 ²
Flexural Modulus (23°C)	3000	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy notched impact strength			ISO 179/1eA ²
-30°C	6.00	kJ/m ²	
23°C	7.00	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	45	kJ/m ²	
23°C	65	kJ/m ²	
Notched Izod Impact Strength (23°C)	6.00	kJ/m ²	ISO 180

Notes

¹ Typical properties: these are not to be construed as specifications.

² Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！