

# Ultramid® 7423-2 NF3001 (Cond)

Polyamide 66

BASF Corporation

## Product Description

Ultramid 7423-2 NF3001 is an impact modified, 13% glass reinforced, heat stabilized injection molding PA6/6.

## General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber Reinforcement, 13% Filler by Weight
Additive	• Heat Stabilizer • Impact Modifier
Features	• Heat Stabilized • Impact Modified
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Mechanical	Nominal Value	Unit	Test Method
Tensile modulus	4000	MPa	ISO 527-2 <sup>2</sup>
Tensile Stress (Break)	86.0	MPa	ISO 527-2 <sup>2</sup>
Tensile Strain (Break)	10	%	ISO 527-2 <sup>2</sup>
Flexural Modulus (23°C)	3500	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy notched impact strength			ISO 179/1eA <sup>2</sup>
-30°C	5.00	kJ/m <sup>2</sup>	
23°C	14.0	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179
-30°C	81	kJ/m <sup>2</sup>	
23°C	83	kJ/m <sup>2</sup>	
Notched Izod Impact Strength (23°C)	14.0	kJ/m <sup>2</sup>	ISO 180

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！