

# Ultramid® B 3ZG6 BK30564

Polyamide 6

BASF Corporation

## Product Description

Ultramid B3ZG6 BK30564 is an impact-modified, pigmented black, 30% glass fiber reinforced injection molding PA6 grade for industrial items having very high impact strength and rigidity.

## General

Material Status	• Commercial: Active
Availability	• Europe • North America
Filler / Reinforcement	• Glass Fiber Reinforcement, 30% Filler by Weight
Additive	• Heat Stabilizer • Impact Modifier
Features	• Good Abrasion Resistance • Good Stiffness • Low Temperature Toughness • Good Chemical Resistance • Good Thermal Aging Resistance • Low Viscosity • Good Dimensional Stability • Good Toughness • Oil Resistant • Good Flow • Heat Stabilized • Semi Crystalline • Good Impact Resistance • High Rigidity • Good Processability • Impact Modified
Uses	• Automotive Applications • Housings • Lawn and Garden Equipment • Electrical Housing • Industrial Applications • Power/Other Tools
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding
Multi-Point Data	• Creep Modulus vs. Time (ISO 11403-1) • Isothermal Stress vs. Strain (ISO 11403-1) • Shear Modulus vs. Temperature (ISO 11403-2) • Isochronous Stress vs. Strain (ISO 11403-1) • Secant Modulus vs. Strain (ISO 11403-1) • Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value	Unit	Test Method
Density	1330	kg/m <sup>3</sup>	ISO 1183 <sup>2</sup>
Water Absorption			
24 hr, 23°C	2.0	%	ISO 62
Saturation	6.2	%	ISO 62 <sup>2</sup>
Equilibrium	2.0	%	ISO 62 <sup>2</sup>

Mechanical	Nominal Value	Unit	Test Method
Tensile modulus	8720	MPa	ISO 527-2 <sup>2</sup>
Tensile Stress (Break)	150	MPa	ISO 527-2 <sup>2</sup>
Tensile Strain (Break)	3.2	%	ISO 527-2 <sup>2</sup>
Flexural Modulus (23°C)	7840	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy notched impact strength (23°C)	14.0	kJ/m <sup>2</sup>	ISO 179/1eA <sup>2</sup>
Notched Izod Impact Strength (23°C)	17.0	kJ/m <sup>2</sup>	ISO 180

Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	220	°C	ISO 3146

Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.080	%
Rear Temperature	245 to 275	°C
Middle Temperature	260 to 285	°C
Front Temperature	270 to 295	°C
Nozzle Temperature	270 to 295	°C
Processing (Melt) Temp	270 to 295	°C
Mold Temperature	80.0 to 95.0	°C
Injection Pressure	3.50 to 12.5	MPa
Injection Rate	Fast	

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

**Ultramid® B 3ZG6 BK30564**  
**Polyamide 6**  
**BASF Corporation**

Wednesday, December 16, 2009

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

---

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！